

Radiant heaters

Basic values:

Parameter	Value
Dimensions	75 x 14.7 x 4.4 mm
Heated area	50 x 14.7 x 4.4 mm
T _{max}	1 000 °C

Details of Standard, 230 V:

Description

Heating elements made of silicon nitride are very suitable as radiation heaters. The almost black silicon nitride used for the heating elements is a long-wave infrared radiator with a maximum radiation emission ($\epsilon > 0.8$) between 8 and 11 μm at 1 000 °C. Thus, a wide variety of materials can be heated effectively by radiation: Sheet metals to be selectively heated or held at temperature for subsequent re-forming processes, as well as plastics where the weld edges are to be melted for a subsequent sealing process. In addition, plastics can be selectively "glued", or sharp edges can be rounded or thermally deburred by radiant heat. Radiation heaters with the dimensions 75 mm x 14.7 mm x 4.4 mm are available in a large number of different power ratings. With open convection and radiation into air at room temperature, many of these heating elements are designed so that they reach their target temperature when operated at nominal voltage without additional control technology. However, they can also be equipped with sensor boreholes for thermocouples, in order to be able to precisely control the temperature of the heating element. The robust design of these heating elements, in conjunction with the good oxidation resistance of the silicon-nitride ceramics, ensures a long service life - both during continuous operation and during cyclic demand.

- surface as fired

Parameter	Value			
Article no.	GLZ 100 094	GLZ 100 130	GLZ 100 128	GLZ 100 109
Nominal power (hot)	190 W \pm 20 W	200 W \pm 20 W	230 W \pm 30 W	260 W \pm 30 W
Nominal voltage	230 V	230 V	230 V	230 V

Basic Material

Parameter	Scale unit	Si ₃ N ₄
max. temperature (T _{max})	°C	1 000
thermal conductivity (l)	W/mK	40
temperature shock resistance (ΔT)	K	500
emissivity (1 100 °C) (ε)	-	0.96
Young's modulus (E)	GPa	320
bending strength (δ _{BB})	MPa	400
compressive strength (δ _D)	MPa	2 000
coefficient of thermal expansion (α)	10 ⁻⁶ K ⁻¹	3
density (g)	g/cm ³	3.21
specific heat (c _p)	J/kgK	750
porosity (100 - % t.D.)	%	0
critical stress intensity factor (K _{IC})	MPa m ^{1/2}	6
Weibull - modulus (m)	-	7.9

The thermal shock resistance depends on the geometric shape of the heater.

Electrical parameters

Parameter	Scale unit	Si ₃ N ₄
resistivity	Ω cm	5 · 10 ⁻³ - 5 · 10 ⁻¹
isolation resistivity	Ω mm (20 °C)	10 ¹³
dielectric strength	kV/mm	25

Emission spectrum

Fully ceramic heating elements are long-wave infrared heaters with a maximum emission of 5 to 10 μm and a radiation coefficient of ε > 0.9.



