

## Hot plates

---

### Basic values:

| Parameter        | Value          |
|------------------|----------------|
| Dimensions       | Ø 100 x 7.0 mm |
| Heated area      | Ø 100 x 7.0 mm |
| T <sub>max</sub> | 500 °C         |

---

### Details of Standard:

#### Description

With a diameter of 100 mm, the heating element of the QEB type is suitable for the relatively large-scale heating of round bodies. The low thermal expansion of silicon nitride helps to make sure that even at 500 °C, only a very small thermal distortion occurs in the heating element and the heat transfer area remains smooth.

\* The actual power depends on resistance, temperature and voltage.

| Parameter             | Value       |
|-----------------------|-------------|
| Article no.           | FLR 100 128 |
| Resistance @ 20 °C    | 50 Ω ±25 %  |
| Nominal voltage       | 230 V       |
| Nominal power @ 20 °C | 1 058 W*    |

## Basic Material

| Parameter                                           | Scale unit                       | Si <sub>3</sub> N <sub>4</sub> |
|-----------------------------------------------------|----------------------------------|--------------------------------|
| max. temperature (T <sub>max</sub> )                | °C                               | 1 000                          |
| thermal conductivity (l)                            | W/mK                             | 40                             |
| temperature shock resistance (ΔT)                   | K                                | 500                            |
| emissivity (1 100 °C) (ε)                           | -                                | 0.96                           |
| Young's modulus (E)                                 | GPa                              | 320                            |
| bending strength (δ <sub>BB</sub> )                 | MPa                              | 400                            |
| compressive strength (δ <sub>D</sub> )              | MPa                              | 2 000                          |
| coefficient of thermal expansion (α)                | 10 <sup>-6</sup> K <sup>-1</sup> | 3                              |
| density (g)                                         | g/cm <sup>3</sup>                | 3.21                           |
| specific heat (c <sub>p</sub> )                     | J/kgK                            | 750                            |
| porosity (100 - % t.D.)                             | %                                | 0                              |
| critical stress intensity factor (K <sub>IC</sub> ) | MPa m <sup>1/2</sup>             | 6                              |
| Weibull - modulus (m)                               | -                                | 7.9                            |

The thermal shock resistance depends on the geometric shape of the heater.

---

## Electrical parameters

| Parameter             | Scale unit   | Si <sub>3</sub> N <sub>4</sub>              |
|-----------------------|--------------|---------------------------------------------|
| resistivity           | Ω cm         | 5 · 10 <sup>-3</sup> - 5 · 10 <sup>-1</sup> |
| isolation resistivity | Ω mm (20 °C) | 10 <sup>13</sup>                            |
| dielectric strength   | kV/mm        | 25                                          |

---

## Emission spectrum

Fully ceramic heating elements are long-wave infrared heaters with a maximum emission of 5 to 10 μm and a radiation coefficient of ε > 0.9.



